

Especificaciones Arena Sílica

Malla	NW-35	NW-40	NW-45	NW-50	NW-55	NW-60	U-85
20	0	0	0	0	0	0	0
30	2.5	1	0.5	0.5	0	0	0
40	45	31	5	5	4	1	1
50	46.5	45	47	36	30	19	4
70	5	19	41	41	40	35	14
100	0.9	3	6	14	20	33.4	41
140	0.1	1	0.5	3	5	10	30
200	0	0	0	0.5	1	1.5	9
270	0	0	0	0	0	0.1	1
PAN	0	0	0	0	0	0	0
AFS-GFN	33-38	37-42	42-49	47-53	52-58	57-63	75-90

Característica		Composición Química	
PH	6.0 - 8.5	%SIO2	99.8
ADV(ML)	0 - 5	% AL2O3	0.08
%LOI	0.1	%FE2O3	0.03
TIPO GRANO	Redondo	%TIO2	≤ 0.01
		%CAO2	≤ 0.01
		%MGO	≤ 0.01